



IPC/JEDEC J-STD-033C

Handling, Packing, Shipping and Use of Moisture/Reflow Sensitive Surface Mount Devices

A joint standard developed by the JEDEC JC-14.1 Committee on Reliability Test Methods for Packaged Devices and the B-10a Plastic Chip Carrier Cracking Task Group of IPC

Supersedes:

IPC/JEDEC J-STD-033B.1
includes Amendment 1 -
January 2007
IPC/JEDEC J-STD-033B -
October 2005
IPC/JEDEC J-STD-033A -
July 2002
IPC/JEDEC J-STD-033 -
April 1999
JEDEC JEP124
IPC-SM-786A - January 1995
IPC-SM-786 - December 1990

Users of this standard are encouraged to participate in the development of future revisions.

Contact:

JEDEC
Solid State Technology Association
3103 North 10th Street, Suite 240-S
Arlington, VA 22201-2107
Tel 703 907.0026
Fax 703 907.7501

IPC
3000 Lakeside Drive, Suite 309S
Bannockburn, Illinois
60015-1249
Tel 847 615.7100
Fax 847 615.7105

Table of Contents

1 FOREWORD	1	3.3.2 Materials	4
1.1 Purpose	1	3.3.3 Labels	6
1.2 Scope	1	3.3.4 Moisture Barrier Bag Sealing	6
1.3 Assembly Processes	1	3.3.5 Dry-Pack Precautions	6
1.3.1 Mass Reflow	1	3.3.6 Shelf Life	7
1.3.2 Localized Heating	1	4 DRYING	7
1.3.3 Socketed Components	1	4.1 Post Exposure to Factory Ambient	7
1.3.4 Point-to-Point Soldering	1	4.1.1 Any Duration Exposure	7
1.3.5 Aqueous Cleaning	1	4.1.2 Short Duration Exposure	10
1.4 Reliability	2	4.2 General Considerations for Baking	10
1.5 Terms and Definitions	2	4.2.1 High Temperature Carriers	10
1.5.1 Active Desiccant	2	4.2.2 Low Temperature Carriers	10
1.5.2 Bar Code Label	2	4.2.3 Paper and Plastic Container Items	10
1.5.3 Bulk Reflow	2	4.2.4 Bakeout Times	10
1.5.4 Carrier	2	4.2.5 ESD Protection	10
1.5.5 Desiccant	2	4.2.6 Reuse of Carriers	10
1.5.6 Floor Life	2	4.2.7 Solderability Limitations	10
1.5.7 Humidity Indicator Card (HIC)	2	5 USE	11
1.5.8 Manufacturer's Exposure Time (MET)	2	5.1 Incoming Bag Inspection	11
1.5.9 Moisture-Barrier Bag (MBB)	2	5.1.1 Upon Receipt	11
1.5.10 Moisture-Sensitive Identification (MSID)	2	5.1.2 Component Inspection	11
1.5.11 Rework	2	5.2 Floor Life	11
1.5.12 Shelf Life	2	5.3 Safe Storage	11
1.5.13 SMD	2	5.3.1 Dry Pack	11
1.5.14 Solder Reflow	2	5.3.2 Shelf Life	11
1.5.15 Water Vapor Transmission Rate (WVTR)	3	5.3.3 Dry Atmosphere Cabinet	11
2 APPLICABLE DOCUMENTS (Normative)	3	5.4 Reflow	12
2.1 American Society for Testing and Materials (ASTM)	3	5.4.1 Opened MBB	12
2.2 Electronic Industries Alliance (EIA, JEDEC)	3	5.4.2 Reflow Temperature Extremes	12
2.3 IPC Standards	3	5.4.3 Additional Thermal Profile Parameters	12
2.4 Joint Industry Standards	3	5.4.4 Multiple Reflow Passes	12
2.5 Department of Defense	3	5.4.5 Maximum Reflow Passes	12
3 DRY PACKING	3	5.5 Drying Indicators	12
3.1 Requirements	3	5.5.1 Excess Humidity in the Dry Pack	12
3.2 Drying of SMD Packages and Carrier Materials Before Being Sealed in MBBs	3	5.5.2 Floor Life or Ambient Temperature/ Humidity Exceeded	13
3.2.1 Drying Requirements - Levels 2a - 5a	3	5.5.3 Level 6 SMD Packages	13
3.2.2 Drying Requirements for Carrier Materials	4	6 BOARD REWORK	13
3.2.3 Drying Requirements	4	6.1 Component Removal, Rework, and Remount ..	13
3.2.4 Excess Time Between Bake and Bag	4	6.1.1 Removal for Failure Analysis	13
3.3 Dry Pack	4	6.1.2 Removal and Remount	13
3.3.1 Description	4	6.2 Baking of Populated Boards	13

7 DERATING DUE TO FACTORY ENVIRONMENTAL CONDITIONS 13

APPENDIX A Test Method for Humidity Indicator Card used with Electronic Component Packaging 15

APPENDIX B Derivation of Bake Tables 16

APPENDIX C Changes in J-STD-033C 17

Figures

Figure 3-1 Typical Dry-Pack Configuration for Moisture-Sensitive SMD Packages in Shipping Tubes 4

Figure 3-2 Humidity Indicator Card (HIC) (Example) 5

Figure 3-3 Moisture-Sensitive Identification Label (Example) 6

Figure 3-4 Moisture-Sensitive Caution Label (Example) 6

Figure 3-5 MBB with No Evacuation (Example) 7

Figure 3-6 MBB with Recommended Light Air Evacuation (Example) 7

Figure 3-7 MBB with Too Much (Full) Evacuation (Example) 7

Figure A-1 Photo of Testing Apparatus 15

Tables

Table 3-1 Dry Packing Requirements 4

Table 3-2 Typical HIC Spot Compliance 6

Table 4-1 Reference Conditions for Drying Mounted or Unmounted SMD Packages (User Bake: Floor life begins counting at time = 0 after bake) 8

Table 4-2 Default Baking Times Used Prior to Dry-Pack that were Exposed to Conditions ≤60% RH (MET = 24 h) 9

Table 4-3 Resetting or Pausing the “Floor Life” Clock at User Site 9

Table 5-1 Moisture Classification Level and Floor Life 11

Table 7-1 Recommended Equivalent Total Floor Life (days) @ 20 °C, 25 °C & 30 °C, 35 °C For ICs with Novolac, Biphenyl and Multifunctional Epoxies (Reflow at same temperature at which the component was classified) Maximum Percent Relative Humidity 14

Handling, Packing, Shipping, and Use of Moisture/ Reflow and/or Process Sensitive Components

1 FOREWORD

The advent of surface mount devices (SMDs) introduced a new class of quality and reliability concerns regarding damage from the solder reflow process, such as cracks and delamination. This document describes the standardized levels of floor-life exposure for moisture/reflow sensitive SMDs along with the handling, packing, and shipping requirements necessary to avoid moisture/reflow related failures. Companion documents J-STD-020 and J-STD-075 define the classification procedure and JEP113 defines the labeling requirements.

For moisture sensitivity, moisture from atmospheric humidity enters permeable packaging materials by diffusion. Assembly processes used to solder SMDs to printed circuit boards (PCBs) expose the entire package body to temperatures higher than 200 °C. During solder reflow, the combination of rapid moisture expansion, materials mismatch, and material interface degradation can result in cracking and/or delamination of critical interfaces within the device.

Typical solder reflow processes of concern for all devices are infrared (IR), convection/IR, convection, vapor phase reflow (VPR), hot air rework tools, and wave solder, including full immersion.

Non-semiconductor devices may exhibit additional process sensitivities beyond moisture sensitivity such as thermal sensitivity, flux sensitivity, or cleaning process sensitivity.

1.1 Purpose The purpose of this document is to provide manufacturers and users with standardized methods for handling, packing, shipping, and use of moisture/reflow and process sensitive devices that have been classified to the levels defined in J-STD-020 or J-STD-075. These methods are provided to avoid damage from moisture absorption and exposure to solder reflow temperatures that can result in yield and reliability degradation. By using these procedures, safe and damage-free reflow can be achieved. The dry-packing process defined herein provides a minimum shelf life of 12 months from the seal date.

1.2 Scope This standard applies to all devices subjected to bulk solder reflow processes during PCB assembly, including plastic encapsulated packages, process sensitive devices, and other moisture sensitive devices made with moisture-permeable materials (epoxies, silicones, etc.) that are exposed to the ambient air.

1.3 Assembly Processes

1.3.1 Mass Reflow This standard applies to bulk solder reflow assembly by infrared (IR), convection/IR, convection, and vapor phase reflow (VPR) processes. It does not apply to bulk solder reflow processes that immerse the component bodies in molten solder (e.g., wave soldering bottom mounted components). Such processes are not allowed for many SMDs and are not covered by the component qualifications standards used as a basis for this document.

1.3.2 Localized Heating This standard also applies to moisture/reflow sensitive SMD packages that are removed or attached singly by local ambient heating, i.e., hot air rework. (Refer to Clause 6.)

1.3.3 Socketed Components This standard does not apply to SMD packages that are socketed and not exposed to solder reflow temperatures during either bulk reflow or rework of adjacent devices. Such SMD packages are not at risk and do not require moisture precautionary handling.

1.3.4 Point-to-Point Soldering This standard does not apply to SMD packages in which only the leads are heated to reflow the solder (e.g., hand-soldering, hot bar attach of gull wing leads, and through hole by wave soldering). The heat absorbed by the package body from such operations is typically much lower than for bulk surface mount reflow or hot air rework and moisture precautionary measures are typically not needed.

1.3.5 Aqueous Cleaning For non-cavity SMDs, typical short term aqueous cleaning processes will not impact the floor life (internal moisture content). Special consideration should be given to non-hermetic cavity packages.